	<spe< td=""><td>CIFICA</td><td>TION></td><td></td></spe<>	CIFICA	TION>	
			SPEC.No. AS	DIQ-SPE-051(00) n. 8, 2022
То:				
	CUSTOM	ER'S PRODUCT N	IAME	
		DDUCT NAME: 45N-SERIES		
RECEIPT CONFIRM	MATION			
	DITIONAL CONSENT		CONDITIONAL CO	DNSENT
	APPROVED		CHECKED	
ASDI SIGNATURE				
	APPROVED Xianglong Li	CHECKED Liang Wang	PREPARED Jiayin Cai	



REV.	DATE	DESCRIPTION	APPROVED	CHECKED	PREPARED
00	Jan. 8, 2022	New release	Xianglong Li	Liang Wang	Jiayin Cai

CAUTION WHEN HANDLING

Before use the products, please read this specification.

CAUTION FOR SAFETY USING

When use the products, be careful to mentioned below for safety using.

CAUTION

*The product should be used within 12 monthes.

Focus on the storage conditions.

Solderability may become weak if it exceeds the period.

*Do not use and store the product in condition of gas corrosion

(Salt, Acid, Alkaline).

*The products must be preheated before soldering.

The operating temperature including self-generated heat must be within - $25 \sim +125 ^{\circ}$ C.

*Rework by soldering iron;Please keep the mentioned conditions in this specification.

*In case of insert P.C. Board on chassis, do not add mechanical stress to the product.

*Be careful to arrange of non-magnetic field type inductors.

The error may be caused by magnetic field coupling.

*In case handle the products, please use wrist strap for ground static discharge on human body.

The product keeps away from magnet or magnetized things.

*Do not use the product beyond the mentioned conditions in this specification.

*About an application

The products listed on this specification sheet are intended for use in general electronic equipment

(AV equipment, telecommunications equipment, home appliances, amusement equipment, computer equipment, personal equipment, office equipment, measurement equipment, industrial robots) under a normal operation and use condition.

*The products are not designed or warranted to meet the requirements of the applications listed below, whose performance and/or quality require a more stringent level of safety or reliability, or whose failure, malfunction or trouble could cause serious damage to society, person or property. Please understand that we are not responsible for any damage or liability caused by use of the products in any of the applications below or for any other use exceeding the range or conditions set forth in this specification sheet.

1)Aerospace/Aviation equipment
2)Military equipment
3)Seabed equipment
4)Safety equipment
5)Medical equipment
9)Transportation control equipment
7)Power-generation control equipment
which directly endanger human life
8)Atomic energy-related equipment
9)Other applications that are not

considered general-purpose applications

If you intend to use the products in the following applications, please contact our sales office.

Transportation equipment (cars, electric trains, ships, etc.), Public information-processing equipment, Electric heating apparatus / burning equipment, Disaster prevention/crime prevention equipment

When using this product in general-purpose applications, you are kindly requested to take into consideration securing protection circuit/equipment or providing backup circuits, etc., to ensure higher safety.

Xiamen ASDI Electronics Co.,Ltd.	DWG.No. ASDIQ-SPE-051(00)	ISSUE	
----------------------------------	------------------------------	-------	--

CUSTOMER	ASDI PART No.	CUSTOMER'S DWG NO.
Each Corporation	AMPI6045N-SERIES	

1.INDEX

Listed item	Attachment&Tables	Page
1.Features	Please see (1)	3/8
2.Dimensions	Please see (2)	3/8
3.Part Numbering	Please see (3)	3/8
4.Electrical Specifications	Please see (4)	3/8
5.Material List	Please see (5)	5/8
6.Reliability Tests	Please see (6)	5/8
7.Soldering	Please see (7)	7/8
8.Packaging Information	Please see (8)	7/8
9.Note	Please see (9)	8/8

2.Manufacturing Location

China

DWG.No.	ASDIQ-SPE-051(00)	PAGE 2/8		
Xiamen ASDI Electronics Co.,Ltd.				


(1)Features

1. This specification applies Low Profile Power Inductors. 2.100% Lead(Pb) & Halogen-Free and RoHS compliant.





(2)Dimensions



Series	A(mm)	B(mm)	C(mm)	D(mm)	E(mm)	F(mm)
AMPI6045N	6.0±0.3	6.0±0.3	4.2±0.3	1.65REF	2.7REF	4.9REF

(3)Part Numbering

AMPI 6045 1R0 N С Е В D Α

A: Series

B: Dimension

C: Control S/N

D: Inductance 1R0=1.0µH

E: Inductance Tolerance M=±20%; N=±30%

(4)Electrical Specifications Table 1

ASDI Part Number	Inductance (μH)	Tolerance (%)	Test Frequency	DCR (mΩ) MAX	Isat(A) △L/L0:≦ 35%	Irms(A) (rise to40 °CMAX)
AMPI6045N-1R0N	1.00	±30%	100kHz/1V	18.0	9.85	5.10
AMPI6045N-1R5N	1.50	±30%	100kHz/1V	25.0	7.00	5.00
AMPI6045N-2R2N	2.20	±30%	100kHz/1V	30.0	6.00	4.90
AMPI6045N-3R3M	3.30	±20%	100kHz/1V	35.0	5.25	3.70
AMPI6045N-4R7M	4.70	±20%	100kHz/1V	38.0	5.00	3.30
AMPI6045N-5R6M	5.60	±20%	100kHz/1V	42.0	4.40	3.15
AMPI6045N-6R8M	6.80	±20%	100kHz/1V	60.0	3.80	3.00
AMPI6045N-100M	10.0	±20%	100kHz/1V	68.0	3.20	2.45
AMPI6045N-150M	15.0	±20%	100kHz/1V	95.0	2.60	2.05
AMPI6045N-220M	22.0	±20%	100kHz/1V	125	2.05	1.80
AMPI6045N-270M	27.0	±20%	100kHz/1V	156	1.90	1.70
AMPI6045N-330M	33.0	±20%	100kHz/1V	188	1.65	1.40
AMPI6045N-470M	47.0	±20%	100kHz/1V	300	1.30	1.25
AMPI6045N-680M	68.0	±20%	100kHz/1V	450	1.00	0.85
AMPI6045N-101M	100.0	±20%	100kHz/1V	680	0.80	0.55
AMPI6045N-121M	120.0	±20%	100kHz/1V	780	0.80	0.80
AMPI6045N-151M	150.0	±20%	100kHz/1V	910	0.75	0.70
AMPI6045N-181M	180.0	±20%	100kHz/1V	1088	0.72	0.60
AMPI6045N-221M	220.0	±20%	100kHz/1V	1400	0.65	0.55
AMPI6045N-102M	1000	±20%	100kHz/1V	7000	0.36	0.30
AMPI6045N-222K	2200	±10%	100kHz/1V	16900	0.15	0.06


Notes

 $\label{eq:lambda} \begin{tabular}{ll} \textbf{Isat: Based on inductance change} & $(\triangle L/L0: \le -30\%)$ @ ambient temp. 25° \\ \textbf{Irms: Based on temperature rise} & $(\triangle T: 40^{\circ}$C typ.)$ \\ \end{tabular}$

DWG.No.	ASDIQ-SPE-051(00)	PAGE 3/8
oLtd.		

Xiamen ASDI Electronics Co


Core chipping



Туре	L	w
AMPI6045N	4.5mm Max.	4.5mm Max.


Vacant appearance tolerance Limit

Size of vacancies occurring to coating resin is specified below.



External appearance specification for exposed wire

Exposed end of the winding wire at the secondary side should be 3mm and below.



Exposed wire tolerance limit of coating resin part on product side. Size of exposed wire occurring to coating resin is specified below. 1.Width direction(dimension a): Acceptable when a \leq 1/2W

Nonconforming when a > w1/2W

2.Length direction(dimension b): Dimension b is not specified.
3.When total area of exposed wire occurring to each sides is not greater than 50% of coating resin area, that is acceptable.

	DWG.No.	ASDIQ-SPE- 051(00)	PAGE 4/8
Xiamen ASDI Electronics Co.,Ltd.			

(5)Material List



No.	Items	Materials
1	Core	Ni-Zn ferrite
2	Wire	Copper Wire
3	Coating	Ероху
4	Solder	Lead free

(6)Reliability Tests


No.	Test item	Performance	Test details
1	Operating temperature	- 25 ~ +125℃.	Including self-generated heat
2	Storage Temperature	$-40 \sim +85^{\circ}\mathrm{C}$ 5 to $40^{\circ}\mathrm{C}$ for the product with taping.	
3	Rated current		
4	Inductance (L)	Within the specified tolerance	LCR Meter: HP 4285A or equivalent, 100kHz, 1V
5	DC Resistance		DC Ohmmeter: HIOKI3227 or equivalent
6	Temperature characteristics	Inductance change: Within±20%	Measurement of inductance shall be taken at temperature rang within–25°C to +85°C. With reference to inductance value at+20°C,change rate shall be calculated. Measurement of inductance shall be taken at temperature rang within–40°C to +125°C. With reference to inductance value at+20°C,change rate shall be calculated.
7	Resistance to flexure substrate	No damage	The test samples shall be soldered to the testing board by the reflow. As illustrated below, apply force in the direction of the arrow indicating until deflection of the test board reaches to 2mm. Results
8	Adhesion of Terminal electrode	Shall not come off PC board.	The test samples shall be soldered to the testing board and by the reflow. 10 N, 5 s Applied force: 10 N to X and Y directions. Duration: 5s Solder cream thickness: 0.15
9	Resistance to Vibration	Inductance change: Within±10% No abnormality observed in appearance.	The test samples shall be soldered to the test board by the reflow. Then it shall be submitted to below test conditions. Frequency: 10-55Hz Total Amplitude: 1.5mm (May not exceed acceleration 196m/S2) Sweeping Method:10Hz to 55Hz to 10Hz for 1min. Time: 2 hours each in X,Y, and Z Direction. Recovery: At least 2hrs of recovery under the standard condition after the test, followed by the measurement within 48hrs.

	DWG.No.	ASDIQ-SPE-051(00)	PAGE 5/8
Xiamen ASDI Electronics Co.,Ltd.			


No.	Test item	Performance Test details		
10	Solderability	At least 90% of surface of terminal electrode is covered by new solder. The test samples shall be dipped in flux, a immersed in molten solder as shown in be Flux: methanol solution containing rosin 2 Solder temperature: 245±5°C Time: 5±1.0 sec. Immersion depth: All sides of mounting te shall be immersed.		
11	Resistance to soldering	Inductance change: Within±10% No abnormality observed in appearance.	The test sample shall be exposed to reflow oven at 230±5℃ for 40 seconds, with peak temperature at 260±5℃ for 5 seconds,2 times. Test board thickness: 1.0mm Test board material: glass epoxy-resin	
12	Thermal shock		The test samples shall be soldered to the test board by the reflow. The test samples shall be placed at specified temperature for specified time by step 1 to step 4 as shown below in sequence. The temperature cycles shall be repeated 100 cycles. Phase Temperature(C) Time(min.) 1 -40±3*C 30±3 2 Room Temp Within 3 3 85±2*C 30±3 4 Room Temp Within 3	
13	Damp heat life test	Inductance change: Within±10%	Test Method and Remarks The test samples shall be soldered to the test board by the reflow. The test samples shall be placed in thermostatic oven set at specified temperature and humidity as shown in below. Temperature: 60±2°C Humidity: 90~95%RH Time: 500+24/-0 hrs	
14	Loading under damp heat life test	No abnormality observed in appearance.	The test samples shall be soldered to the test board by the reflow. The test samples shall be placed in thermostatic oven set at specified temperature and humidity and applied the rated current continuously as shown in below. Temperature: 60±2°C Humidity: 90~95%RH Applied current: Rated current Time: 500+24/-0 hrs	
15	Low temperature life test		The test samples shall be soldered to the test board by the reflow. After that, the test samples shall be placed at test conditions as shown in below. Temperature:-40±2°C Time:500+24/-0 hrs	
16	Loading at high temperature life test		The test samples shall be soldered to the test board by the reflow. Temperature: 85±2°C. Applied current: Rated current Time: 500+24/-0 hrs.	

DWG.No.	ASDIQ-SPE- 051(00)	PAGE 6/8

(7)Soldering



(8)Packaging Information 8-1,Reel Dimension




Туре	A(mm)	B(mm)	C(mm)	D(mm)
AMPI6045N	16.4±2	100±4.0	13.2±0.2	330±2.0

DWG.No. ASDIQ-SPE-051(00) PAGE 7/8

COVER TAPE

Xiamen ASDI Electronics Co.,Ltd.

8-2, Tape Dimension



Series	A(mm)	B(mm)	Ko(mm)	P(mm)	W(mm)	t(mm)
AMPI6045N	6.40±0.1	6.40±0.1	4.65±0.1	12.0±0.1	16±0.3	0.4±0.05

8-3, Packaging Quantity

Туре	Chip / Reel
AMPI6045N	1000

(9)Note

·Storage Conditions

- To maintain the solderability of terminal electrodes:

 1. ASDI products meet IPC/JEDEC J-STD-020D standard-MSL, level 1.
- 2. Temperature and humidity conditions: Temperature: 5 to 30deg.C, Humidity: 75% Max.
- 3. Recommended products should be used within 12 months form the time of delivery.
- 4. The packaging material should be kept where no chlorine or sulfur exists in the air.
- ·Transportation
- 1. Products should be handled with care to avoid damage or contamination from perspiration and
- 2. The use of tweezers or vacuum pick up is strongly recommended for individual components.
- 3. Bulk handling should ensure that abrasion and mechanical shock are minimized.

8/8	DWG.No.	ASDIQ-SPE-051(00)	PAGE 8/8
-----	---------	-------------------	-------------